



CARBON WELDED PIPE - ASTM A53				
Dimensions and Weights				
NPS Designator	OD, in.	Wall Thickness, in.	lb/ft	Schedule
1/8"	0.405	0.068	0.240	40
		0.095	0.310	80
1/4"	0.540	0.088	0.430	40
		0.119	0.540	80
3/8"	0.675	0.091	0.570	40
		0.126	0.740	80
1/2"	0.840	0.109	0.850	40
		0.147	1.090	80
3/4"	1.050	0.113	1.130	40
		0.154	1.480	80
1"	1.315	0.133	1.680	40
		0.179	2.170	80
1-1/4"	1.660	0.140	2.270	40
		0.191	3.000	80
1-1/2"	1.900	0.145	2.720	40
		0.200	3.630	80
2"	2.375	0.154	3.660	40
		0.218	5.030	80
2-1/2"	2.875	0.203	5.800	40
		0.276	7.670	80
3"	3.500	0.216	7.580	40
		0.300	10.260	80
3-1/2"	4.000	0.226	9.120	40
		0.318	12.520	80
4"	4.500	0.237	10.800	40
		0.337	15.000	80
5"	5.563	0.258	14.630	40
		0.375	20.800	80
6"	6.625	0.280	18.990	40
		0.432	28.600	80
8"	8.625	0.322	28.580	40
		0.500	43.430	80

The information listed is correct to the best of our knowledge. Wisconsin Steel & Tube Corporation assumes no responsibility for errors or omissions. Wisconsin Steel & Tube Corporation publishes this for guidance of their customers and reserves the right to add or delete items without notification.